Drypower

RECHARGEABLE SEALED LEAD ACID BATTERY

12SB160CL-FR (12V 160Ah)

SPECIFICATIONS

Nominal Voltage (V)

12V

Nominal Capacity

 20 hour rate
 (8.01A to 9.90V)
 160.2Ah

 10 hour rate
 (15.8A to 9.90V)
 158.0Ah

 5 hour rate
 (26.9A to 9.60V)
 134.5Ah

 1 hour rate
 (90.0A to 9.60V)
 90.0Ah

Weight

Approx. 46kg (101.2lbs)

Internal Resistance (@1kHz)

Approx. 4mΩ

Maximum Discharge Current

For 5 seconds

1500A

Charging Methods @25°C (77°F)

Cycle Use:

Charging Voltage 14.4V to 15.0V

Coefficient -5.0mV/°C/Cell

Maximum Charging Current 45A

Standby Use:

Float Charging Voltage 13.50V to 13.80V

Coefficient -3.0mV/°C/Cell

Design Life 12 years

Operating Temperature Range

Charge -15°C (5°F) to +40°C (104°F) Discharge -15°C (5°F) to +50°C (122°F) Storage -15°C (5°F) to +40°C (104°F)

Charge Retention (Shelf Life) @20°C (68°F)

 1 month
 98%

 3 months
 94%


 6 months
 85%

Case Material UL94-V0 Flame Retardant

Terminal F16


Description of Torque Value of Hard Ware for the Terminals

Recommended Torque Value M6: 5.39 N-m (55kg-cm) Max. Allowable Torque Value M6: 8.82 N-m (90kg-cm)



DIMENSIONS


mm (inch)














Effect of Temperature on Capacity 25°C(77°F)



Trickle (or float) Service Life







- PERFORMANCE DATA

Discharge Rates in Watts to Various End Voltages at 25°C(77°F)

Time	End Voltage	1.85V	1.80V	1.75V	1.70V	1.67V	1.65V	1.60V
5	min	3365	3754	4094	4386	4528	4675	4955
10	min	3008	3273	3431	3584	3655	3730	3872
15	min	2656	2810	2921	3029	3079	3131	3223
30	min	1551	1633	1694	1753	1776	1801	1845
60	min	927	981	1019	1045	1053	1062	1076
120	min	503	534	551	565	571	579	591
180	min	412	439	453	466	472	479	488
240	min	336	354	365	373	376	380	386
300	min	289	301	309	316	318	321	325
600	min	171	178	184	189	190	193	196
1200	min	90.6	93.4	95.9	98.1	99.2	100	101

- Discharge Rates in Amperes to Various End Voltages at 25°C(77°F)

Time	End Voltage	1.85V	1.80V	1.75V	1.70V	1.67V	1.65V	1.60V
5	min	296	373	417	446	459	472	490
10	min	245	276	303	325	335	346	363
15	min	218	246	265	278	283	289	306
30	min	119	131	141	149	152	155	160
60	min	70.7	79.6	82.8	85.2	86.5	87.9	90.0
120	min	37.5	44.2	45.9	47.1	47.6	48.2	49.1
180	min	32.6	36.2	37.5	38.6	39.1	39.6	40.2
240	min	25.8	28.7	29.8	30.7	31.0	31.3	31.7
300	min	23.9	24.8	25.5	26.1	26.2	26.6	26.9
600	min	14.4	15.0	15.3	15.5	15.6	15.8	15.9
1200	min	7.43	7.62	7.76	7.90	7.95	8.01	8.06

All data on the spec. sheet is an average value:

The tolerance range : X < 6min(+15% - 15%), $6min \le X < 10min(+12\% - 12\%)$, $10min \le X < 60min(+8\% - 8\%)$, $X \ge 60min(+5\% - 5\%)$